

# AIMTILE POOL

CEMENTITIOUS WATER RESISTANT TILE ADHESIVE FOR SWIMMING POOL

## DESCRIPTION

AIMTILE POOL is a premium tile adhesive specifically formulated for swimming pools and other water features. This high-performance adhesive is designed to provide exceptional bonding strength, durability, and resistance to water exposure, making it an ideal choice for both indoor and outdoor pool tiling applications.

## USES

Adhesion of the following Tile Types:

- ▶ Mosaic
- ▶ Ceramic Tiles & Porcelain tile
- ▶ Terrazzo
- ▶ Quarry
- ▶ Marbles
- ▶ Granite

## APPLICATION AREAS

Wall and Floor  
Exterior and Interior  
Substrates: Cement  
Wet area such as swimming pool, fish pond, fountain, spa and sauna

## ADVANTAGES

- ▶ Thin or thick bed fixing
- ▶ Tile on tile applications on existing flooring
- ▶ Excellent adhesion to even on non-porous substrates
- ▶ Suitable for bonding on facades
- ▶ Excellent resistance to water and humidity
- ▶ Waterproof – permanent immersion does not affect adhesion
- ▶ Excellent bonding even in damp conditions
- ▶ Slump and slip resistance
- ▶ Easy and economical to use
- ▶ Excellent workability
- ▶ Low VOC emission
- ▶ Extended open time
- ▶ Deformable

## APPLICATION

### Coverage

Solid bed fixing: 3mm-6mm depth 5.5-11kg/m<sup>2</sup>  
Notch trowel: smooth surface 2kg/m<sup>2</sup>

### Instructions for use

Mix AIMTILE POOL in a ratio of 6 to 7 liters of water per 25kgs bag and 4.5 to 5.5 for 20kgs Bag. Mix to a uniform lump-free consistency. Leave for approximately 5 minutes to allow the resins to completely dissolve. Moisten the support if necessary, but never the tiles. Mixing should be by a force action mixer. Hand mixing is recommended for small quantities only.

### Point to be noted:

The open curing time of tile adhesive at 30°C is approximately 30 minutes. Therefore care should be taken in preparing the mortar. Prepare only the surface, which can be tiled within this time. AIMTILE POOL should not be used on painted or metal surface.

### Method of Application

Apply AIMTILE POOL to a uniform thickness of 3mm to 6mm on the support to cover the slots on the back of the tiles, of an area of not more than 1m<sup>2</sup> at a time.

For horizontal applications a solid bed fixing is recommended as well as for heavy-duty vertical applications.

For other vertical applications, use a toothed spatula to comb horizontally to remove excess. The trowel should have 6mm notches at 25mm intervals center to center.

Apply the tiles, press it, and smooth out carefully so that the mortar is spread evenly. If the bonding is perfect, the tile will not slide. The joints can be filled with AIMGROUT (available in gray, white or matching colors on request).



# AIMTILE POOL



## CONSUMPTION

Approximately 2kg/m<sup>2</sup> depending on the support. Clean the tools with water after use. Store in dry conditions and protect against wind and rain

## PACKING AND STORAGE

Shelf life: AIMTILE POOL can be kept for 12 months in unopened packs.

Packaging: 15, 20 & 25 KG Bags

## SAFETY

AIMTILE POOL is formulated without any hazardous substances. However, as with all construction chemical products, it is important to exercise caution. When handling AIMTILE POOL, it is recommended to wear protective clothing such as gloves and goggles. For maximum safety, wearing a long sleeve overall, safety shoes, and a face mask is also advised. After each use, reseal the containers and store the product according to the safety instructions on the label. In case of contact with the skin or eyes, immediately rinse with fresh water. If any of the product is accidentally swallowed, do not induce vomiting, but seek immediate medical assistance. For more detailed information, please consult the Material Safety Data Sheet (MSDS) provided.

## TECHNICAL SPECIFICATIONS

Classification	C2TE
Aspect	Powder
Color	Grey, White
Density	1.5gm / c.c. app
Flash point	Not applicable
Std. conforms to	EN 12004, ISO 13007, ANSI A 118.1
Tensile strength	Part 7: 1985: 2.85N/mm <sup>2</sup> :(BS 6319)
Flexural strength	4.5N/mm <sup>2</sup> :(BS 6319: Part 3: 1990)
Adhesion strength (28 days)	ASTM D4541:2001: >2.5N/mm <sup>2</sup>
Pot life (hrs)	>6
Adjustment time (min)	>30
Open time (min)	>20
Grouting time on wall (hrs)	8
Grouting time on floor( hrs)	24
Application temperature (C)	5-40
VOC Content in g/L	<1

The information given in this datasheet is based on both current development work and many years of field experience. Whilst every effort is made to ensure that the information is reliable, we cannot accept responsibility for any work carried out with our materials as we have no control over methods of application, site, conditions, etc.



Al Mutathawir Insulation Materials Industries L.L.C.  
T: +971 6 5345585 | F: +971 6 5347717  
E: info@aim-insu.com | W: www.aim-insu.com  
P.O. Box: 22704, Sharjah-UAE