

NOVASEAL PLAIN/MINERAL

DESCRIPTION

- ▶ NOVASEAL is the standard roofing and waterproofing membrane, reinforced either with a core of non-woven polyester of 200g/m² nominal weight (referred to as P) or a 50g/m² fiberglass fleece (referred to as F). It is the recommended roofing membrane, but can be useful for another variety of applications among them; large slabs, terraces, bathrooms, wet areas, foundations, basements, tanking and others. NOVASEAL is manufactured in a standard size of 1x10m for thickness of 3mm, 4mm and 5mm and 1x20m for 2mm, however special length can be done on request. All rolls are sold in pallets and covered with a shrink wrap.

ADVANTAGES

- ▶ Positive barrier to water and dampness.
- ▶ Excellent resistance to ageing and atmospheric agents.
- ▶ Remains flexible even in cool weather.
- ▶ Maintains shape stability at high temperatures.
- ▶ Accommodates structural movements.
- ▶ Maybe torched directly over old shingles or old bituminous membranes.
- ▶ The membrane comes in various types according to the surface top:
 - ▶ SAND: The top surface is covered with fine sand
 - ▶ PBS: The top surface is covered with a thin easy torched Poly-ethylene film.
 - ▶ SL: The top surface is covered with reflective slates either in natural grey or pigmented in various colors.
 - ▶ The bottom surface is covered with a thin easy torched Poly-ethylene film.
- ▶ Resistant to water-borne chemical attack.

APPLICATION

TOOLS & EQUIPMENT

The application of the NOVASEAL membrane requires very limited tools like propane gas torches and cylinder, a knife for cutting the membrane to size and a trowel with rounded end.

COATING MIXTURE OF THE MEMBRANE

The waterproofing capability is provided by the coating mix of the NOVASEAL membrane. The reinforcement is impregnated with this mix and then coated to factory regulated thickness from 2mm to 5mm depending on reinforcement and client requirement. The mix is made up of bitumen, modified with Amorphous Poly-olefins, thermoplastic resins and stabilizers giving the membrane its excellent resistance to atmospheric agents and ageing, maintaining shape stability at high temperatures, improving adhesion strength and making the membrane easy to apply saving on time and labor.

METHOD OF STATEMENT

The application of NOVASEAL is both easy and quick. For application on concrete, tiles or any other porous surface, coat the substrate with ADVAPRIM (solvent based bituminous primer according to ASTM D41) at the rate of 4–5m²/liter. Allow the coating to dry thoroughly. In time of high humidity we recommend it should be left overnight. The NOVASEAL should first be unrolled and positioned correctly. Each roll should overlap the adjacent roll by 10cm. Once the roll has been positioned correctly, the membrane should be rolled up again, taking care not to change its orientation. Using left to right movements, heat the lower surface of the membrane with a propane gas torch. This will cause slight surface melting and the molten bitumen will adhere to the surface. You then torch on the side overlap to the recommended size of 100mm. Continue the above method for consecutive rolls remembering end-laps must be minimum 200mm. Inspection of lap joints must be carried out to ensure total adhesion.

NOVASEAL PLAIN/MINERAL

TECHNICAL SPECIFICATIONS

NOVASEAL products are tested at random intervals by independent laboratories to international standards and the results of these tests are available on request. In addition, each batch manufactured is subject to strict quality control procedures to ensure it meets appropriate and applicable standards and/or norms.



ASTM		PROCEDURE	UNITS	TOLERANCE	VALUE
Length			m	< - 1%	10
Width			m	< - 1%	1
Thickness		ASTM D5147	mm	-0.2mm	4.00
Tensile Properties: Max. Tensile Force	- long	ASTM D5147	N/5mm	-20%	850
	- trans	ASTM D5147	N/5mm	-20%	700
Tensile Properties: Elongation	- long	ASTM D5147	%	-15	45
	- trans	ASTM D5147	%	-15	50
Resistance to Tearing	- long	ASTM D5147	N	min	550
	- trans	ASTM D5147	N	min	375
Lap Joint Strength	- long	ASTM D5147	N/5mm	-20%	750
	- trans	ASTM D5147	N/5mm	-20%	550
Low Temperature Flexibility*			°C	min	0 to -5
Dimensional Stability at +80°C	- long	ASTM D5147	%	mlv	-0.5
	- trans	ASTM D5147	%	mlv	-0.5
Water Absorption		ASTM D5147	%	mlv	<0.15

CE		PROCEDURE	UNITS	TOLERANCE	VALUE
Visible Defects		EN 1850-1	N°/m²	0	0
Length		EN 1848-1	m	< - 1%	10
Width		EN 1848-1	m	< - 1%	1
Straightness		EN 1848-1	mm	<20mm	pass
Mass Per Unit Area		EN 1849-1	kg/m²	± 10%	4.70
Thickness		EN 1849-1	mm	-0.2mm	4.00
Water Tightness to Liquid Water		EN 1828-1	mlv	>60 kPa	Pass
Tensile Properties: Max. Tensile Force	- long	EN 12311-1	N/5cm	-20%	850
	- trans	EN 12311-1	N/5cm	-20%	700
Tensile Properties: Elongation	- long	EN 12311-1	%	-15	-15
	- trans	EN 12311-1	%	-15	-15
Resistance to Tearing (nail shank)	- long	UNI 8202/-	N	min	175
	- trans	UNI 8202/-	N	min	190
Shear Resistance of Joint	- long	EN 12317-1	N/5cm	-20%	750
	- trans	EN 12317-1	N/5cm	-20%	550
Resistance to Static Loading (Method A)		EN 12730	kg	min	20
Resistance to Impact		EN 12691	mm	mlv	>700
Flexibility at Low Temperature*		EN 1109	°C	min	0 to -5
Dimensional Stability	- long	EN 1107-1	%	max	-0.5
Flow Resistance less than 2mm		EN 1110	°C	mlv	100
Reaction to fire		EN 13501-1		Euroclass	F

*Different Cold Flexibility values can be supplied to special order.

The information given in this datasheet is based on both current development work and many years of field experience. Whilst every effort is made to ensure that the information is reliable, we cannot accept responsibility for any work carried out with our materials as we have no control over methods of application, site, conditions, etc.



Al Mutathawir Insulation Materials Industries L.L.C.
T: +971 6 5345585 | F: +971 6 5347717
E: info@aim-insu.com | W: www.aim-insu.com
P.O. Box: 22704, Sharjah- UAE